



# TPC 65A

## TYPICAL PHYSICAL PROPERTIES

### PHYSICAL PROPERTIES

### POLYETHER BASED ELASTOMER

HARDNESS SHORE A _____	62-67
TENSILE PSI _____	2640
100% MODULUS PSI _____	280
300% MODULUS PSI _____	645
ELONGATION % _____	440
DIE C TEAR PLI _____	180
BASHORE REBOUND _____	7
COMPRESSION SET% _____ (METHOD B, 22 hrs @ 158°F)	6